

## AquaMAX<sup>®</sup> 1700

### Product description

Downer Blasting Services' (DBS) AquaMAX<sup>®</sup> 1700 High Energy products is a blend of HEAT<sup>®</sup>1700 Emulsion, Ammonium Nitrate and Fuel Oil for use in wet blastholes where higher energy blasting is required.

These products are pumped into the blast holes to displace water.

The benefits of the AquaMAX<sup>®</sup> 1700 range include:

- Excellent safety characteristics
- Excellent water resistance, which enables extended sleep time in wet holes
- Ability to chemically gas to various in-hole densities to meet specific blast requirements as well as ground conditions
- High-shock energy, which leads to excellent fragmentation in hard ground conditions
- Ability to tailor product type on-bench to suit the ground conditions and blast requirements

### Application

AquaMAX<sup>®</sup>1700 products are high-energy bulk explosives ideal for wet blast holes.

- AquaMAX<sup>®</sup>1700 products can be used in wet blastholes containing static water; ideally these holes should be fired within 14 days of loading
- Blastholes with dynamic water should be loaded and fired as soon as possible, however extra precautions may be required
- Blastholes should only be stemmed after completion of the gassing reaction
- AquaMAX<sup>®</sup>1700 products should not be loaded into areas with reactive and /or hot ground conditions
- Consult your technical representative for site-specific applications

### Specifications (stated at 100MPa)

Properties	ANFO	AquaMAX <sup>®</sup>		
		AM 1760	AM 1770	AM 1780
<b>Product identification</b>				
<b>Effective energy<sup>1</sup> (MJ/kg)</b>	2.3	2.7	2.6	2.6
<b>Relative weight strength<sup>1</sup> (%)</b>	100	117	114	112
<b>Relative bulk strength<sup>1</sup> (%)</b>	100	183	179	174
<b>Velocity of detonation (VoD) range<sup>2</sup> (km/s)</b>	3.0-4.5	4.2-5.7	4.2-5.6	4.2-5.5
<b>Nominal density range<sup>3</sup> (g/cm<sup>3</sup>)</b>	0.7-0.85	1.05-1.25	1.05-1.25	1.05-1.25
<b>Minimum hole diameter (mm)</b>	60	75	75	75
<b>Maximum down hole life in dry conditions</b>	4 weeks	4 weeks	4 weeks	4 weeks

1. Downer Blasting Services' energy values, relative weight strength and relative bulk strength are calculated by an ideal detonation modeling computer program at the Imperial College London, United Kingdom.
2. Range of VoD measured in –situ in medium hard rock and hole diameters between 102 and 270 mm.
3. A number of factors affect final product density including in-hole conditions, ammonium nitrate density, emulsion density and the amount of gassing etc. The AquaMAX<sup>®</sup> range of products is able to be gassed to a cup density ranging from 0.95 to 1.25g/cm<sup>3</sup>.

## AquaMAX<sup>®</sup> 1700

### Classification

UN No.	0241
Shipping name	EXPLOSIVE, BLASTING, TYPE E
Class	1.1D
Safety Data Sheet	AquaMAX

### Recommendations for use

**Priming Requirements:** The preferred primer is a 400g cast booster. It is recommended that an additional cast booster be used every 12 metres of column charge to reduce risks associated with explosive column disruption.

**Packaging:** AquaMAX<sup>®</sup> 1700 is available in bulk and is delivered through bulk truck delivery systems.

**Handling:** Information regarding this product is available from the relevant SDS.

**Transportation:** All explosives are classified as Dangerous Goods and must be transported in accordance with relevant State and Commonwealth regulations.

**Storage and Security:** All explosives are classified as Dangerous Goods and must be stored and secured in accordance with relevant State and Commonwealth regulations.

### Manufacturer

**Downer EDI Mining – Blasting Services Pty Ltd**

**ABN:** 97 009 687 487

**A:** 22 Cordelia Street  
South Brisbane

**P:** + 61 7 3026 6666

**F:** + 61 7 3026 6070

**1800 680 402 (Emergency contact- Australia)**

DISCLAIMER: All information contained in this data sheet is accurate, complete and up-to-date at the time of issue. Whilst Downer EDI Mining - Blasting Services Pty Ltd ("DBS") has made every reasonable effort to ensure the accuracy of the information; every user is responsible for its own understanding and the safe and correct use of the products. It is the sole responsibility of the user to make enquiries, obtain advice and determine the necessary safe conditions for the product's intended use and the user assumes liability for any loss, damage, expense or cost resulting from such use. To the extent permitted by law, DBS expressly disclaims any and all liability arising from the use, or reliance upon the information contained in this data sheet.